

Product Name CI Name	CI Number	Mass Tone	Tint Tone (1:10)	Light Fastness		Heat Stability in °C for 10 min	Oil Absorption g/100g	Bleeding Resistance (Scale 1~5 where 1 = Poor & 5 = Excellent)							Recommended Applications - PAINTS						
				Xenon Arc (Blue Wool Scale 1-8) (1 = Poor & 8 = Excellent)				Xylene	Ethanol	Ethyl Acetate	MEK	Water	Acid 5% HCL	Alkali 5% NaOH	Soap Solution	Air Drying	Stoving	Waterbase	Automotive	Powder Coating	
				Full Tone	Tint Tone																
Rubine Toner B PR 57:1	15850:1			3 - 4	3	210	48	4	4	4-5	4-5	4	2	2-3	2	•					
Rubine Toner Y PR 57:1	15850:1			3 - 4	3	210	50	4	4	4-5	4-5	4	2	2-3	2	•					
Rubine Toner 6BP PR 57:1	15850:1			3 - 4	3	240	51	4	4	4-5	4-5	4	2	2-3	2	•	•				
Red F2R PR 2	12310			4	4	140	51	3-4	3-4	3	3	5	5	5	5	•					
Toludine Red B PR 3	12120			6	4	140	61	4	4-5	4	3	5	5	5	5	•					
Toludine Red Y PR 3	12120			6	4	140	61	4	4-5	4	3	5	5	5	5	•					
Signal Red B PR 4	12085			6	5-6	140	55	4	4	4	4	4	5	5	5	•					
Signal Red Y PR 4	12085			6	5-6	140	58	4	4	4	4	4	5	5	5	•					
Red FRR PR 12	12385			4	4	140	68	4-5	5	4	3-4	3-4	2	5	5	•	•	•			
Red 2B Calcium PR 48:2	15865:2			5-6	5	220	56	5	5	4	4	5	5	5	5	•					
Red 2B Manganese PR 48:4	15865:4			7	6	250	64	5	5	5	5	5	5	5	5	•	•	•			
Red Lake CRL PR 53:1	15585:1			2	2	200	56	4-5	4-5	4-5	4-5	3	4-5	4-5	4	•					
Red FGR PR 112	12370			7-6	6	140	61	4-5	5	4	3-4	5	5	5	5	•					
Red TK5R PR 170	12475			8	7-8	250	51	5	5	5	5	5	5	5	5	•	•	•	•	•	•
Red C1701 PR 170	12475			8	7-8	250	68	5	5	5	5	5	5	5	5	•	•	•	•	•	•
Yellow G PY 1	11680			6	5	140	61	4-5	4-5	4	4	4	5	5	5	•					
Yellow 10G PY 3	11710			7-6	6	140	58	4-5	4-5	4	4	4	5	5	5	•					
Yellow LFY PY 65	11740			5-6	5-6	180	78	3	2-3	3-4	3	3	5	5	5	•					
Yellow 5G PY 74	11741			6	5	200	48	4	5	4	4	5	5	5	5	•	•	•			•
Yellow 2G PY 74	11741			6	5	200	51	4	5	4	4	5	5	5	5	•	•	•			•
Yellow HR PY 83	21108			7-8	7	200	61	5	5	5	5	5	5	5	5	•	•	•	•	•	•

Product Name CI Name	CI Number	Mass Tone	Tint Tone (1:10)	Light Fastness		Heat Stability in °C for 10 min	Oil Absorption g/100g	Bleeding Resistance (Scale 1-5 where 1 = Poor & 5 = Excellent)								Recommended Applications - PAINTS				
				Xenon Arc (Blue Wool Scale 1-8) (1 = Poor & 8 = Excellent)				Xylene	Ethanol	Ethyl Acetate	MEK	Water	Acid 5% HCL	Alkali 5% NaOH	Soap Solution	Air Drying	Stoving	Waterbase	Automotive	Powder Coating
				Full Tone	Tint Tone															
Orange 5PA PO 5	12075			6	5	140	51	4-5	4-5	4	3	3	5	5	5	•	•			
Orange G PO 13	21110			4	3	200	51	4	5	4	4	5	5	5	5	•	•			•
Orange RL PO 34	21115			5-4	4	200	58	5	5	5	5	5	5	5	5	•	•	•		•
Blue 15:0 PB15:0	74160			8	7-8	280	48	5	5	5	5	5	5	5	5	•	•	•	•	•
Blue 15:1HS PB15:1	74160			8	7-8	290	51	5	5	5	5	5	5	5	5	•	•	•	•	•
Blue 15:3GS PB15:3	74160			8	7-8	280	55	5	5	5	5	5	5	5	5	•	•	•		•
Blue 15:3RS PB15:3	74160			8	7-8	280	55	5	5	5	5	5	5	5	5	•	•	•		•
Green 7YS PG7	74260			8	7-8	280	38	5	5	5	5	5	5	5	5	•	•	•	•	•
Green 7BS PG7	74260			8	7-8	280	38	5	5	5	5	5	5	5	5	•	•	•	•	•
Violet RL PV 23	51319			8	7-8	220	78	5	5	5	5	5	5	5	5	•	•	•		•
Middle 2231 PY34	77603			8	7-8	240	24	5	5	5	5	5	5	5	5	•	•	•		•
Middle Chrome PY34	77603			8	7-8	200	25	5	5	5	5	5	5	5	5	•	•	•		•
Lemon 2221 PY34	77603			8	7-8	240	24	5	5	5	5	5	5	5	5	•	•	•		•
Lemon Chrome PY34	77603			8	7-8	200	25	5	5	5	5	5	5	5	5	•	•	•		•
Primrose Chrome PY34	77603			8	7-8	200	25	5	5	5	5	5	5	5	5	•	•	•		•
Zinc Chrome PY36	77603			8	7-8	200	27	5	5	5	5	5	5	5	5	•	•	•		•
Zinc Chromate PY36.1	77603			8	7-8	200	28	5	5	5	5	5	5	5	5	•	•	•		•
Scarlet YS PR104	77605			8	7-8	220	25	5	5	5	5	5	5	5	5	•	•	•		•
Scarlet BS PR104	77605			8	7-8	220	25	5	5	5	5	5	5	5	5	•	•	•		•
Scarlet 2BS PR104	77605			8	7-8	220	27	5	5	5	5	5	5	5	5	•	•	•		•

Colour Reproduction : For technical reasons connected with color reproduction, the colors shown may not exactly match the pigment colors and do not represent a particular finish. • = Recommended
Tint Shade are reproduced with ratio of Pigment : Titanium Dioxide = 1:10